

Report Number: 2020-753-538Rev2

Prepared for: Hemway
Unit N1
Gildersome Spur
Industrial Estate
Leeds
LS27 7JZ

Sample described as: Hemway Clear Matt Lacquer


No. of samples: 1 **Reference number(s):** HEMCML

Date received: 30/03/2021 **Date(s) tested:** 08-29/04/2021

I **certify** that the above mentioned samples have been tested in accordance with the standard(s) specified below and that they comply or otherwise as follows:

EN 71-3:2019	Complies
---------------------	-----------------

Please see the following pages for details.



Joanne Maggs
Analytical Services Manager

Date: 21st April 2021
Amended: 6th May 2021 to add CrVI results
Amended: 7th May 2021 to change the address

Subcontracted to an ILAC accredited laboratory within the Eurofins group
The reported results relate exclusively to the tested sample

Eurofins Product Testing Services Limited
Unit 16 Willan Trading Estate, Waverley Road
Sale M44 7AY
Tel: +44 (0)161 868 7600
Fax: +44 (0)161 868 7699

Registered Office:
i54 Business Park, Valiant Way
Wolverhampton, WV9 5GB
Registration Number: 7401660
Vat Number: 887 1276 83

Report Number: 2020-753-538Rev2

EN 71-3:2019 Safety of Toys - Migration of certain 19 elements

Limits of element migration from accessible parts of toy material
All figures quoted as mg soluble element per kg material

Element	B	Al	Cr(III) Cr(VI)	Mn	Co	Ni	Cu	Zn	As	Se	Sr	Cd	Sn	Organic tin	Ba	Hg	Pb	Sb
Limits Category I (dry, brittle, powder like, pliable) mg/kg	1200	5625	37,5 0,02	1200	10,5	75	622,5	3750	3,8	37,5	4500	1,3	15000	0,9	1500	7,5	2	45
Limits Category II (liquid, sticky) mg/kg	300	1406	9,4 0,005	300	2,6	18,8	156	938	0,9	9,4	1125	0,3	3750	0,2	375	1,9	0,5	11,3
Limits Category III (scraped-off) mg/kg	15000	70000	460 0,053	15000	130	930	7700	46000	47	460	56000	17	180000	12	18750	94	23	560
Description of sample	Results of analysis																	
A Hemway Clear Matt Lacquer Cat <input type="checkbox"/> I Cat II <input type="checkbox"/> Cat III <input checked="" type="checkbox"/>	0,29	4,3	total Cr 0,07 0,02	0,1	<0,05*	<0,25*	1	0,94	<0,05*	<0,5*	<0,25*	<0,05*	<0,08*		0,68	0,13	<0,05*	<0,25*

* Limit of quantification

^a measured with GC/MS

Chrom (VI): Metrohm: 930 Compact IC flex

Test results and evaluation relate to the tested items only.

Report Number: 2020-753-538Rev2

Analytical details (EN 71-3 clause 10)

10f Technique used: Inductively coupled plasma

10h Notes for individual sample portions -
the following notes apply to the samples indicated and referenced above:

	Applicable samples:
Between 10 and 100mg taken:	N/A
Sample/volume ratio exceeds 1:50:	N/A
Base material included:	N/A
Samples sieved:	N/A
2M HCl added:	N/A
6M HCl added:	N/A
n-heptane used:	N/A
Samples centrifuged:	N/A
Specimens adjusted to 0.3M:	N/A
Less than 10mg present:	N/A
Others:	N/A

****END OF REPORT****