

Intertek Centre Court Meridian Business Park Leicester LE19 1WD UK Tel +44 1162 630330 consumergoods.uk@intertek.com intertek.com

TEST REPORT

NUMBER: LTR24050240B2 Amendment

APPLICANT: Hemway DATE: 23 January 2025

Unit N1

Gildersome Spur Industrial Estate

Leeds LS27 7JZ

SAMPLE DESCRIPTION: Hi White Interior Paint Acrylic Matt (11070)

Medium Interior Paint Acrylic Matt (11071) Transparent Interior Paint Acrylic Matt (11074)

Neutral Exterior Paint Masonry (7532)

White Exterior Paint Masonry (7528)

This is an amendment of LTR24050240B1, originally issued 10 July 2024.

RETAILER: Not specified

SAMPLE RECEIVED: 30 May 2024

PURCHASE ORDER: None

TEST REQUEST:	CONCLUSION:
**EN 71-3 : 2019 + A1 : 2021 - Migration of certain elements	Pass

Tests marked (^) in this report are included in the scope of accreditation of the sub-contractor who performed the test. Tests marked (*) in this report are not included in our UKAS scope of accreditation.

Tests marked (**) in this report are not included in the scope of accreditation of the sub-contractor who performed the test. Opinions, interpretations and comments expressed herein are outside the scope of accreditation.

GEORGE CARTER
Project Manager
Hardlines





TEST REPORT

NUMBER: LTR24050240B2 Amendment

19 Toxic Element Migration Test

Test Method : EN 71-3 : 2019 + A1 : 2021. Acid extraction method was used and toxic elements content were

determined by Inductively Coupled Argon Plasma Spectrometry and Ion Chromatography-

Inductively Coupled Plasma-Mass Spectrometry and/or Gas Chromatographic - Mass Spectrometry

Category (III): Scraped-off toy material:

	Result (mg/kg)			Limit
	(1)	(2)	(3)	(mg/kg)
Soluble Aluminium (Al)	660	<300	<300	28130
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	100	<10	<10	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	<10	<10	38	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	<5.0	12
Soluble Zinc (Zn)	<100	<100	<100	46000



UK



TEST REPORT

NUMBER: LTR24050240B2 Amendment

	Result(mg/kg)		Limit
	(4)	(5)	(mg/kg)
Soluble Aluminium (Al)	<300	<300	28130
Soluble Antimony (Sb)	<10	<10	560
Soluble Arsenic (As)	<10	<10	47
Soluble Barium (Ba)	<10	<10	18750
Soluble Boron (B)	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	130
Soluble Copper (Cu)	<10	<10	7700
Soluble Lead (Pb)	<10	<10	23
Soluble Manganese (Mn)	37	24	15000
Soluble Mercury (Hg)	<10	<10	94
Soluble Nickel (Ni)	<10	<10	930
Soluble Selenium (Se)	<10	<10	460
Soluble Strontium (Sr)	<100	<100	56000
Soluble Tin (Sn)	<10	<10	180000
Soluble Organic tin ++	<5.0	<5.0	12
Soluble Zinc (Zn)	<100	<100	46000

mg/kg = milligram per kilogram

++: Unless the test result was marked with " Δ ", Organic tin content was not directly determined and was derived from migration result of total tin.

Organic tin test result was expressed as tributyl tin.

Chromium (III) value was calculated as difference between migration results of total Chromium and Chromium (VI) .

Tested Components:

- (1) White paint (11070 Hi white interior paint acrylic matt).
- (2) White paint (11701 Medium interior paint acrylic matt).
- (3) Ivory paint (11074 Transparent interior paint acrylic matt).
- (4) Ivory paint (7532 Neutral exterior paint masonry).
- (5) White paint (7528 White exterior paint masonry).

Date of Testing: 12-25 June 2024







Intertek Centre Court Meridian Business Park Leicester LE19 1WD UK

TEST REPORT

NUMBER: LTR24050240B2 Amendment



END OF REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you and all results relate only to the sample tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

